



baresque.com.au
e info@baresque.com.au
p 1300 306 399

FLEXTEX

technical details

<u>Technical Information</u>	Test	Results
Fire Retardant	AS/NZ53837	GROUP 1
QUV		Minimum 100 hours
Solvent Resistance		50 MEK
Humidity		12 hrs 96-100% RH @ 40 degrees C on MDF
MEK Double Rubs/Crockmeter		Withstands 70 cycles
Impact Resistance	ASTM D5420	89 Joules/cm
Abrasion Resistance		5000

Stain Resistance Properties

Group 1 - Brushed Aluminum, Paintable, Argents
 Group 2 - Mirror, Mirror Blue
 Group 3 - Mirror Gold
 Group 4 - Brushed Copper

N = no change
 S = slight change
 M = medium change
 L = large change

Stain Resistance Testing		Group 1		Group 2		Group 3		Group 4	
#	Materials	24 Hrs	7 Day	24 Hrs	7 Day	24 Hrs	7 Day	24 Hrs	7 Day
1	Wesson Oil	N	N	N	N	N	N	N	S
2	Household Ammonia	N	N	N	N	N	N	S	S
3	409 all purpose cleaner	N	N	N	N	N	N	N	N
4	"Tide" laundry detergent	N	N	N	N	N	N	N	N
5	Isopropyl Alcohol	N	N	N	N	N	N	N	N
6	Clorox	N	N	L	L	L	L	L	L
7	Grape Juice	N	N	N	N	N	N	N	N
8	Orange Juice Concentrate	N	N	N	N	N	N	N	N
9	Coffee	N	N	N	N	N	N	N	S
10	Mustard	N	N	N	N	N	N	S	S
11	Ketchup	N	N	N	N	N	N	N	N
12	Red wine	N	N	N	N	N	N	N	N
13	Coca-Cola	N	N	N	N	N	N	N	N
14	Water	N	N	N	N	N	N	N	N
15	Black crayon	N	N	N	N	N	N	N	N
16	Lipstick	N	N	N	N	N	N	N	N
17	Pine-Sol	N	N	N	N	N	N	N	N
18	Vinegar	N	N	N	N	L	L	N	N
19	Steel Wool	N	N	N	N	N	N	N	N
20	Tea	N	N	N	N	N	N	N	N
21	Windex® Surface Cleaner	N	N	N	N	N	N	N	N
22	Scotch-Brite® w/Soap	N	N	N	N	N	N	N	N